

LIONTHANE #550

Technical Data Sheet

Information

This paint is a two-component acrylic urethane paint consisting of acrylic polymer resin and HDI curing agent, and the requirements for materials, chemical resistance, weather resistance, and water resistance are output. It is a paint that is mainly applied to ABS materials and brings a typical image of gloss and color.

Main Ingredient

• Acrylic Polymer Resin

Properties

| | LIONTHANE #550 | | |
|------------------|-------------------------------------------------|--|--|
| Appearance | Metallic | | |
| Viscosity | 65 ± 3 (Stomer KU at 25°c) | | |
| Specific Gravity | 0.99 ± 0.02 | | |
| Solid Content | 37 ± 2 % | | |
| Thickness | 15 ~ 20 µm | | |
| Polish | 80 ~90 (High-gloss top coat transparent coating | | |
| Drying Time | Bottom Coat 70°c X 30 min | | |
| | Top Coat 70°c X 30 min | | |

Field Of Application

• Adhesion to plastic materials is good, especially to ABS materials.







Characteristic

- Excellent water resistance, weather resistance and chemical resistance
- Easy to work with two-component paint
- Repaintable
- High gloss maintained after top coat clear painting
- Paints that do not contain 6 major heavy metals

STORAGE

Products should be kept tighly closed when not in use and stored in a cool, dry place because they will absorb miosture if left in open containers and it could result in increased viscosity, color change and some crystallization of the products.

This product has shelf life of 6 months when protected from moisture and air.

HANDLING PRECAUTION

Please refer to the MSDS for futher information.

SEOEUN Tech CO.

Tel. 82-55-326-4017

Fax. 82-55-326-4018

Standard Application Method

SEOEUN TECH CO.

| Name | | LIONTHANE #550 | Remarks | |
|------|---------------------------------|----------------------|--------------------------------|--|
| 1 | Appearance | COLOR | | |
| 2 | Color | Solid & Metallic | | |
| 3 | Materials | ABS | | |
| 4 | Paint Name | Acrylic Urethane | | |
| 5 | Thinner | Urethane Thinner 740 | | |
| 6 | Hardener | Hardener BS | | |
| 7 | Mixing Ratio (Paint / Hardener) | 100 / 20 | | |
| 8 | Mixing Ratio (Paint / Thinner) | 100 / 40 ~ 60 | Paint / Thinner | |
| 9 | Spray Viscosity | 11 ~ 13 sec | lwata Cup #2 | |
| 10 | Filter | 150 micron | | |
| 11 | Painting Method | Air Spray | Degreasing IPA | |
| 12 | Setting Time | 5 ~ 10 min | at Room Temperature(20 ~ 25μm) | |
| 13 | Baking Condition | 70°c X 30 min | | |
| 14 | Flim Thickness | 15 ~ 20 μm | | |
| 15 | Warranty | 6 Months | | |

Cautions On Handling

- 1) Mix thoroughly the Paint and Thinner with proper stirring device.
- 2) Use specified thinner only, or may result in defects.
- 3) Use adequate ventilation to work area. Avoid prolonged breathing of vapor.
- 4) Store drum in the dark ares with good ventilation.



fice & Factory : 351-9, Dongbuk-ro 473beon-gil, Sangdong-myeon, Gimhae-si Gyeongsangnam-do, Republic c Tel. 82-55-326-4017 Tel. 82-55-326-4017



CERTFICATION OF ANALYSIS

SEOEUN Tech CO.

Customer : Product Name : Lot No. : Quantity :

| Test Item | Unit | Specification | Result | Remarks |
|-----------------|------|---------------|--------|---------|
| Appearance | _ | | | |
| Viscosity | KU | | | |
| Secific Gravity | | | | |
| Solids Content | % | | | |
| Color | _ | | | |

Head office & Factory : 351-9, Dongbuk-ro 473beon-gil, Sangdong-myeon, Gimhae-si Gyeongsangnam-do, Republic of Korea

> Tel. 82-55-326-4017 Fax. 82-55-326-4018

CERTIFY THE ABOVE STATEMENT OF QUALITY TO BE TRUE AND CORRECT.

Head of Quality Control